

T E S T C E R T I F I C A T E

ST-23-12-11-02

Product: Laminate Flooring "YILDIZ ENTEGRE AQUA LAMINATED PARQUET"

Producer: Yıldız Entegre Ağaç Sanayi ve Tic.A.Ş.
Arslanbey O.S.B. Mah. 1. Cadde No:13
41285 Kartepe-Kocaeli
Turkey

Order: Determination of Laminate Flooring Topical Moisture Resistance according to NALFA-Method after 72 hours water load


Test report: 2723602/1

Test results:

For extended 72 hours water load:

Parameter		Wet Swell	Re-dry Swell / Rating	Requirements according NALFA (24 hours)
Final Thickness Swell [mm]	Position 1	0,52	0,39	Not applicable
	Position 2-4	0,31	0,15	Fulfilled
Qualitative Rating Specimen 1/2		4/3	2/1	
Water Leakage		Not detected		Not applicable

Dresden, 11/12/2023



Head of laboratory




Engineer in charge