

Contact person	Date	Reference	Page
Ulrika Johansson Division Materials and Production +46 10 516 53 22 ulrika.johansson@ri.se	2023-11-21	O100785-1221815	1 (2)

YILDIZ ENTEGRE ROMANIA S.A.
Yildiz Street, No. 1
Arges County
RO-117545 Oarja
Rumänien

Formaldehyde emission, IOS-MAT-0181/EN 16516

Assignment

Determination of the formaldehyde emission after 28 days according to EN 16516:2017/A1 in order to fulfil the requirements set out in IOS-MAT-0181 "Formaldehyde requirements of wood-based materials comprised in the German Prohibition of Chemical Ordinance", section 1.4.2 Flat dry process fibreboard.

Test specimen

A sample of 25 mm MDF board, one board approximately 86 x 100 cm. The board was packed in plastic foil and delivered to RISE on October 17, 2023.

Sample information:

Manufacturer: Yildiz Entegre Romania S.A.
Thickness: 25 mm
Production date: 2023-09-30

The test specimen represents the MDF board product type 1: 5.7 – 40 mm.

Method

The test was started on October 17 by unpacking the sample. Two specimens of 300 x 400 mm were cut out from the sample. The edges were partly sealed with aluminium tape leaving 0.36 m/specimen unsealed (1.5 m/m²). The specimens were conditioned outside the testing chamber in a separate conditioning container (with air velocity of approx. 0.2 m/s) in a room with controlled climate conditions of 23 ± 2 °C and 50 ± 5 % RH. The specimens were then placed in the test chamber, four days before the emission test.

Test conditions in the chamber:

Chamber volume: 0.266 m³
Temperature: 23 ± 1 °C
Relative Humidity: 50 ± 3 % RH
Air exchange rate: 0.5 h⁻¹
Air velocity at specimen surface: 0.1 – 0.3 m/s
Area of sample: 0.48 m²
Area specific air flow rate: 0.28 m³/m²h

Place of testing: Chemistry and Applied Mechanics,
Brinellgatan 4, Borås

RISE Research Institutes of Sweden AB

Postal address	Office location	Phone / Fax / E-mail
Box 857 501 15 BORÅS SWEDEN	Brinellgatan 4 504 62 Borås SWEDEN	+46 10-516 50 00 +46 33-13 55 02 info@ri.se

This report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.



Accred. No. 1002
Testing
ISO/IEC 17025

The sampling of formaldehyde was carried out on November 14 with DNPH samplers. Sampled volume was 24 – 32 litres. The determination was performed according to ISO 16000-3:2022, which means analysis on a liquid chromatograph with absorbance detector. Measurement uncertainty is estimated to 36 % (rel). Quantification limit is estimated to 0.06 µg/DNPH sampler.

The analyses were performed on November 17, 2023

Results

The presented results are the determined steady-state concentration (ppm) in the emission chamber:

Sample	Formaldehyde (ppm)		Formaldehyde mean value (ppm)
MDF board 25 mm, Produced 2023-09-30	0.089	0.087	0.088

The formaldehyde concentration in the empty chamber (background-level) was 0.002 ppm which is subtracted.

The results relate only to the items tested.

Evaluation of the test results

Decision rule: When comparing the measured results and requirement level, the average value of the measured results has been compared with the requirement level. No account is taken to the measurement uncertainty.

The result is compared with the requirements of IOS-MAT-0181 “Formaldehyde requirements of wood-based materials comprised in the German Prohibition of Chemical Ordinance”, section 1.4.2 Flat dry process fibreboard:

Board type	Test method	Limit	Test result	Pass/Fail
Flat dry process fibreboard	EN 16516 according to German criteria	0.10 ppm	0.088 ppm	Pass

**RISE Research Institutes of Sweden AB
Chemistry and Applied Mechanics - Chemical Product Safety**

Performed by

Examined by

Ulrika Johansson

Fredrik Solhage

Verification

Transaction 09222115557505175183

Document

O100785-1221815 Yildiz Romania, MDF 19mm, EN 16516

Main document

2 pages

Initiated on 2023-11-21 12:51:59 CET (+0100) by Ulrika

Johansson (UJ)

Finalised on 2023-11-21 13:31:32 CET (+0100)

Signatories

Ulrika Johansson (UJ)

RISE Research Institutes of Sweden AB

Company reg. no. 556464-6874

ulrika.johansson@ri.se

Signed 2023-11-21 12:52:00 CET (+0100)

Fredrik Solhage (FS)

fredrik.solhage@ri.se

Signed 2023-11-21 13:31:32 CET (+0100)

This verification was issued by Scrive. Information in italics has been safely verified by Scrive. For more information/evidence about this document see the concealed attachments. Use a PDF-reader such as Adobe Reader that can show concealed attachments to view the attachments. Please observe that if the document is printed, the integrity of such printed copy cannot be verified as per the below and that a basic print-out lacks the contents of the concealed attachments. The digital signature (electronic seal) ensures that the integrity of this document, including the concealed attachments, can be proven mathematically and independently of Scrive. For your convenience Scrive also provides a service that enables you to automatically verify the document's integrity at: <https://scrive.com/verify>

